
EPISTAR


> Mechanical Specification:

- (1) Dimension
 - Chip size: 9 mil x 9 mil (230±25 μm x 230±25 μm)
 - Thickness: 6.7 mil (170±25 μm)
 - P bonding pad: 3.9 mil (100±10 μm)

(2) Metallization

- Topside P electrode: Au alloy
- Backside N electrode: Au alloy





Features:

- High luminous intensity
- \cdot ITO layer on top

Applications:

- Mobile appliances
- Indoor application
- · Consumer electronic

> Electro-optical Characteristics at 25°C:

| Parameter | Symbol | | Condition | Min. | Тур. | Max. | Unit |
|--------------------------------------|--------|----|-------------|------|------|------|------|
| Forward Voltage | Vf1 | | If = 10μΑ | 1.35 | - | - | V |
| | Vf2 | | If = 20mA | - | 2.05 | 2.4 | V |
| Reverse Current | Ir | | Vr = 10V | - | - | 10 | μΑ |
| Peak Wavelength | λр | | lf = 20mA | - | 591 | - | nm |
| Dominant Wavelength ⁽¹⁾ | λd | | lf = 20mA | 584 | 589 | 594 | nm |
| Spectra Half-width | Δλ | | lf = 20mA | - | 15 | - | nm |
| Luminous Intensity ⁽²⁾⁽³⁾ | | E5 | - If = 20mA | 75 | - | - | mcd |
| | lv | E6 | | 90 | - | - | |
| | | E7 | | 110 | - | - | |
| | | E8 | | 140 | - | - | |

Note:

(1) Basically, the wavelength span is 10nm; however, customers' special requirements are also welcome.

(2) Customers' special requirements are also welcome.

(3) Luminous intensity is measured by EPISTAR's equipment on bare chips.

This product is made and sold under one or more of the following patents: Taiwan Patent Certificate Nos.: 098998; 113696; 128153; 131010; 144415; 148677; 170789; 183481; 183846; U.S. Patent Nos.: 5,008,718; 5,164,798; 5,233,204; 5,789,768; 6,078,064; 6,057,562; 6,225,648; 6,552,367; 6,876,005, and any foreign counterparts.


Condition Unit Parameter Symbol Rating lf **Forward DC Current** Ta = 25°C ≤ 30 mΑ Vr Ta = 25°C ≤ 10 V **Reverse Voltage** °C **Junction Temperature** Тj ≤ 115 _ °C Chip -40 ~ +85 °C Chip-on-tape/storage 5~35 **Storage Temperature** Tstg °C -20 ~ +65 Chip-on-tape/transportation °C **Temperature during Packaging** 280(<10sec)


> Absolute Maximum Ratings:

Note: Maximum ratings are package dependent. The above maximum ratings were determined using a Printed Circuit Board (PCB) without an encapsulant. Stresses in excess of the absolute maximum ratings such as forward current and junction temperature may cause damage to the LED

> Characteristic Curves:










Fig.5 – Dominant Wavelength (20mA) vs. Ambient Temperature




Fig.2 – Forward Current vs. Forward Voltage




Fig.4 – Forward Voltage (@20mA) vs. Ambient Temperature

